



PERFORMANCE SPECIFICATION

FAMOBIT P3

Revised 01/01/03

Famobit P3 is a high-grade polymeric bitumen sheet, modified with age stabilizing amorphous polyalphaolefin (APAO). Polyester reinforcing provides superior strength and flexibility. Superior performance of the modified bitumen compound makes this membrane extremely puncture resistant and provides excellent weather resistance and long term performance. It can be used as an inner-ply sheet or a high performance flashing system.

Composition:

Inlay:	Thermally bonded non-woven polyester
Bottom Side:	Meltable polyethylene film
Top:	Silica sand
Roll Length:	10.0 m (32 ft 9 in)
Roll Width:	1.0 m (3 ft 3 in)
Roll Weight:	32.2 kg (71 lb)
Normal Thickness:	3.0 mm (120 mil)
Quantity/pallet	25 rolls/pallet
	250 m ² (2,691 ft ²)

Technical Data:

Thickness:	3.0 mm (120 mil)
Reinforcement:	Non-woven polyester with unit weight of 250 g/m ² (7.4 oz/yd ²)
Tensile Strength:	MD: >1,000 N/5cm (115 lbf/in) XMD: >1,000 N/5cm (115 lbf/in)
Elongation:	MD: >40% XMD: >40%
Low Temperature Flex:	<-15°C (5°F)
Heat Stability:	>140°C (284°F)
Asbestos Content, %:	Zero

1033 Downshire Chase, Virginia Beach, VA 23452
Telephone: (757) 340-4201 Fax: (757) 431-3172
E-Mail: perrymd@att.net

1033 Downshire Chase, Virginia Beach, VA 23452
Telephone: (757) 340-4201 Fax: (757) 431-3172
E-Mail: perrymd@att.net